

AQUA-PRO

WATERBORNE WOOD FINISH

TECHNICAL DATA

PRODUCT DESCRIPTION

ProCoat® Aqua-Pro™ is a non-yellowing, waterborne acrylic urethane wood finish. Due to new polymerization technology, Aqua-Pro™ can be used as a single or two component. This wood finish develops an extremely durable film with outstanding scuff, mar and chemical resistance. This product exhibits outstanding dry times and adhesion to even the most difficult of substrates. Formulated with eco-friendly premium grade resins, this is the clear choice for an environmentally responsible installer.

TYPICAL PROPERTIES:

Color in Container.....	Clear, White (wet)
Solids Content	33% +/-2%
VOC	<250 g/l
Weight/Gallon	8.60 lbs/gal
COF	0.87 SCOF
Konig Hardness.....	90
Taber CS17 1000g@1000c	45 mg loss
Flash Point	>200°F (93°C)
Odor.....	Mild, Non-Offensive
Sheens.....	Gloss, Semi-Gloss, Satin, Matte
Dry Time	2-4 hours between coats
Clean Up	Water
Coverage	450-600 square feet per gallon
Application	T-Bar, roller, trim pad, brush, spray
Shelf Life	1 year, unopened container

PRODUCT FEATURES:

- ✓ Easy Application
- ✓ Fast Dry Time
- ✓ Exceptional Durability
- ✓ Excellent Adhesion Properties
- ✓ Excellent Flow & Leveling
- ✓ 1-Component or 2-Component
- ✓ Environmentally Friendly
- ✓ V.O.C. Compliant

PRODUCT USES:

- Ideal for wood flooring, cork, concrete & resilient tile
- Formulated for use on newly sanded domestic & exotic woods
- Highly recommended for residential, commercial & sport applications.

RECOMMENDED SYSTEMS:

WOOD: Newly sanded floors: 1 coat ProCoat Splashdown Wood Sealer with 2-3 coats of Aqua-Pro or 3-4 coats of Aqua-Pro. When coating over stains allow stain to dry per manufacturer's directions or longer depending on atmospheric conditions. A test area is recommended to insure compatibility with stain. **Recoating existing surfaces:** Abrade with appropriate screen or conditioning pad and apply 1-2 coats of Aqua-Pro. When recoating existing surfaces compatibility must be determined by applicator.

Continue on page 2

APPLICATION PROCEDURES:

WOOD: Shake coating vigorously for 30 – 45 seconds and then let sit 10 to 15 minutes before applying. Pour a 6" to 8" wide line of finish along the starting wall. Follow the grain of the wood. Draw a clean, pre-dampened applicator forward. Following the grain of the wood, move the finish toward the opposite wall. Hold the applicator at a snowplow angle to maintain a wet edge at all times. (Maintain at least 3" wide wet edge at all times to ensure proper coverage rate.) To prevent lapping and dry marks make sure you're using recommended coverage of 450-500 square foot per gallon. Do not spread too thin. When cutting in floor, never work more than five feet ahead of the person applying the finish. For smoothest results before applying final coat, buff with conditioning pad. Always vacuum and tack thoroughly with a slightly water dampened mop or cloth after abrading.

Roller Application: The use of 10mm or 3/8th microfiber rollers are suggested. Applicator should evaluate the application and use the appropriate roller material and size determined by the porosity of the substrate being coated.

WARRANTY:

If PRO-COAT products are proved defective, the user's exclusive remedy will be at PRO-COATS option to replace the defective PRO-COAT products or to refund the purchase price for the defective quantity. Except for the replacement or refund remedies, PRO-COAT is not liable for direct damages or liable for indirect, incidental or consequential damages, regardless of the legal theory asserted, including negligence and strict liability.